

Technical Data Sheet

Product Name	DYNOdamascus				
Application	Paint Protection Film				
Thickness	190±10μm				
Properties	Properties		Unit	Value	Test Method
	Thickness		μm	190±10	Thickness gauge
	Coating layer crack	MD	mm	54	- ASTM D 412
		TD	mm	55	
	Self-Healing		sec	under 30	Room Temp.
	Adhesion (30 min)		gf/25mm	> 1400	ASTM D3330
	Adhesion (24 hours)		gf/25mm	> 2200	
Product Structure	Self-healing(Pattern) TPU PSA Liner				
Characteristic	- Hydrophobic & Self-Healing- Clear type high gloss finish protection- Gorgeous pattern image with delicate rainbow effect- Anti-Contamination				